

# Classification report

## Classification of thermoplastic wood adhesives for non-structural applications

Test report 505 29381/1e



Clients **Nordcoll A/S**  
Egeskovvej 12

3490 Kvistgård  
Denmark

**Dynea ASA**  
Svelleveien 33

2001 Lillestrøm  
Norway

### Basis

EN 205 : 1991-05  
Test methods for wood adhesives for non-structural applications; determination of tensile shear strength of lap joints

EN 204 : 2001-05  
Classification of thermoplastic wood adhesives for non-structural applications.

Corresponds to the national standards of DIN EN.

Product **Wood adhesive**

Product name **Prefere 6403**

Hardener -

Portion of hardener -

Special features -

### Instructions for use

This test report serves to prove classification to load group D4

Classification according to EN 204



Load group D4

### Validity

The data and results stated refer exclusively to the test specimen tested and described.

Testing of adhesive strength does not render possible any statement on other properties of the tested adhesive determining performance and quality.

Load group	Storage sequence	Min. value acc. to EN 204 in N/mm <sup>2</sup>	Mean value of the adhesive strength in N/mm <sup>2</sup>
D4	1	≥ 10	13.4
D4	3	≥ 4	5.0
D4	5	≥ 4	5.2

### Notes on publication

The **ift** notice "Conditions and notes for the use of **ift** test documents" applies.

The cover sheet can be used as a summary.

ift Rosenheim  
22 February 2005

Ulrich Sieberath  
Director

i. A. Karin Lieb  
Head of Material Testing Department

### Contents

The report comprises a total of 4 pages

- 1 Object
- 2 Procedure
- 3 Detailed results