

# Classification report

of adhesive strength of wood adhesives  
according to WATT 91

Test report 505 29381/2e



Clients **Nordcoll A/S**  
**Egeskovvej 12**

3490 Kvistgård  
Denmark

**Dynea ASA**  
Svelleveien 33

2100 Lillestrøm  
Norway

## Basis

WATT 91 (Wood Adhesives Temperature Test), Determination of length joints tested by tensile test with immersion of temperature according to the guideline of Fachverbandes Klebstoff-industrie e.V. Düsseldorf and ift Rosenheim

Product	Wood adhesive
Product name	Prefere 6403
Hardener	-
Portion of hardener	-
Special features	-

## Instructions for use

This test report may be used for the prove of adhesive strength of length joints in tensile test with a sample temperature of 80°C.

## Validity

The above mentioned data and results relate solely to the tested and described wood adhesive

Testing of adhesive strength does not render possible any statement on other properties of the tested adhesive determining performance and quality.

## Notes on publication

The ift notice „Conditions and notes for the use of ift test documents“ applies.

The cover sheet can be used as a summary.

## Contents

The report contains 4 pages in total

- 1 Object
- 2 Procedure
- 3 Detailed results

## Adhesive strength according to WATT 91



7.8 N / mm<sup>2</sup>

ift Rosenheim  
22 February 2005

Ulrich Sieberath  
Director

i. A. Karin Lieb  
Head of Material Testing Department